




## E501c.lv

Product Data Sheet 2017-01



FireWin

# Knauf Fire protection block - FPB

## Product description

Knauf Fire protection block - FPB is a soft, flexible moulded foam part that is used in the Knauf Firestop system - F, and as a filling block for free areas without penetrating installations in the Knauf Fire protection foam FPF.

### Storage

Store dry in the original packaging.  
Storage temperature: + 5°C to + 30°C

### Method of delivery

Knauf Fire protection Block FPB - 1 (1 pcs), article no. 586162  
Knauf Fire protection Block FPB - 4 (4 pcs), article no. 586522

## Scope of application

Knauf Fire protection block - FPB can be used as mixed penetration seal to EI 120 for rigid walls, rigid floors and flexible walls. Through penetration firestop system for electrical cables, telecommunication cables and optical fibre cables, conduits, as well as flammable and non-flammable pipes.

## Properties

- Easy, fast and clean application
- Low air leakage through penetration
- Low thermal conductivity
- High airborne sound insulation
- Fire resistance up to EI120
- Certified according to ETAG 026-2

Technical details:	
Approval:	ETA-11/0206 and ETA-10/0431
Classification of the reaction to fire in accordance with DIN EN 13501-1:	Class E
Color:	Red-brown
Bulk density:	$\rho = 240 \text{ kg/m}^3$ to $300 \text{ kg/m}^3$
Dimensions:	144 mm x 60 mm x 200 mm (B x H x L)
Testing the fire protection properties under environmental influences:	Use category Z1 (use in indoor areas with high humidity and temperatures $\geq 0 \text{ }^\circ\text{C}$ )
Air permeability:	Q600 = $6.61 \text{ m}^3/(\text{h} \cdot \text{m}^2)$ (at 600 Pa differential pressure) Test standard: EN 1026 (test specimen dimensions 355 x 550 x 200 [mm], tested without penetrating elements)
Resistance to static differential pressure:	Pmax = 3700 Pa Test standard: in accordance with EN 12211 (test specimen dimensions 355 x 550 x 200 [mm], tested without penetrating elements)
Thermal conductivity:	$\lambda = 0.103 \text{ W}/(\text{m} \cdot \text{K})$ Test standard: DIN EN 12667
Airborne sound insulation:	Dn,e,w (C;Ctr) = 68 (- 4; - 11) dB Test standard: EN ISO 717-1 (test specimen dimensions 360 x 360 x 200 [mm], tested without penetrating elements)
Surface Resistivity:	R0 = $2 \times 10^9 \Omega$ Test standard: BGR 132:2003 (2.6), DIN IEC 60167
Microbial metabolic potential:	Inert, fungistatic or bacteriostatic Test standard: DIN EN ISO 846
Continuous contact or ambient temperature:	$\leq 80 \text{ }^\circ\text{C}$

## Note

The following specifications do not represent guaranteed product characteristics. They must, therefore, be regarded exclusively as information intended to serve as guideline values.

### Influence of coating materials and chemicals:

The following paints and occasional, brief influence of chemicals do not cause any changes in the technical fire safety properties:

Coating materials: Dispersion paint, alkyd resin paint, polyurethane acrylic lacquer, epoxy resin lacquer, silicone

Solvent/oil: Trichloroethylene, xylene, acetone, white spirit, butyl acetate, butanol

Gaseous chemicals: Ammonia

Note: Environmental conditions with high humidity levels and/or some coating materials and chemicals can cause minor lightening of the color or changes in color.


### Contact with metals and plastics:

The surface consistency of aluminum, stainless steel, galvanized steel and plastics made of polyethylene and polyvinyl chloride is not affected in a negative way upon contact with Knauf Fire protection block FPB.

### Safety:

Please observe the EC Safety Data Sheet.

SIA Knauf, Daugavas iela 4, Saurieši,  
Stopiņu nov., LV-2118, Latvija

 (+371) 67032999

 [www.knauf.lv](http://www.knauf.lv)

 [info@knauf.lv](mailto:info@knauf.lv)

We reserve the right to make technical changes. The current version is always valid. Our warranty is expressly limited to our products in flawless condition. The stated constructional and structure properties, and characteristic building physics of Knauf systems can solely be ensured with exclusive use of Knauf system components or other products expressly recommended by Knauf. All application quantities and delivery amounts are based on empirical data that are not easily transferable to other deviating areas. All rights reserved. All amendments, reprints and photocopies, including those of excerpts, require our expressed permission.

The stated constructional and structure properties, and characteristic building physics of Knauf systems can solely be ensured with exclusive use of Knauf system components or other products expressly recommended by Knauf.

NOTE: This document becomes invalid when replaced by a new version.